

## Performance Characteristic Sheet

**EFFECTIVE DATE:** April 1, 2023

**MANUFACTURER AND MODEL:**

Make: **SciAps**  
 Models: **Model X-550**  
 X-Ray Source: **Gold (Au) Anode**

### FIELD OPERATION GUIDANCE

**ACTION LEVEL SETTING IN THE INSTRUMENT:** 0.3 mg/cm<sup>2</sup>

**NOTE:** This PCS is not applicable at other Action Level settings; the Action Level setting of the instrument must be 0.3 mg/cm<sup>2</sup> to use this PCS.

**OPERATING PARAMETERS:**

Two-sigma stop mode: average testing time 10-seconds.

**XRF CALIBRATION CHECK LIMITS:**

0.8 to 1.2 mg/cm<sup>2</sup> (inclusive) on NIST SRM 2579 (1.02 mg/cm<sup>2</sup>)/NIST SRM 2573, or equivalent. **Action Level in the instrument must be set to 0.3 mg/cm<sup>2</sup>.**

**SUBSTRATE CORRECTION:**

Not applicable

**INCONCLUSIVE RANGE:**

Au Anode READING DESCRIPTION	SUBSTRATE	INCONCLUSIVE RANGE (mg/cm <sup>2</sup> )
Results not corrected for substrate bias on any substrate	Brick Concrete Drywall Metal Plaster Wood	(0.29 - 0.38) (0.29 - 0.38) (0.29 - 0.38) (0.29 - 0.38) (0.29 - 0.38) (0.29 - 0.38)

## BACKGROUND INFORMATION

### EVALUATION DATA SOURCE AND DATE:

This sheet is supplemental information to be used in conjunction with Chapter 7 of the HUD *Guidelines for the Evaluation and Control of Lead-Based Paint Hazards in Housing*, 2012 Edition ("HUD Guidelines"). Performance parameters shown on this sheet are calculated using test results on building components in the HUD archive. Testing was conducted on 146 test samples in February 2023, each with two separate instruments.

### OPERATING PARAMETERS

Performance parameters shown in this sheet are applicable only when properly operating the instrument using the manufacturer's instructions and procedures described in Chapter 7 of the HUD Guidelines.

### XRF CALIBRATION CHECK:

The calibration of the XRF instrument should be checked using the paint film nearest 1.0 mg/cm<sup>2</sup> in the NIST Standard Reference Material (SRM) used (e.g., for NIST SRM 2579, use the 1.02 mg/cm<sup>2</sup> film; for NIST SRM 2579a, use film 2573 (1.04 mg/cm<sup>2</sup>)).

If the average (rounded to 1 decimal place) of three readings is outside the acceptable calibration check range, follow the manufacturer's instructions to bring the instrument into control before XRF testing proceeds.

### EVALUATING THE QUALITY OF XRF TESTING:

Randomly select ten testing combinations for retesting from each house or from two randomly selected units in multifamily housing.

Conduct XRF re-testing at the ten testing combinations selected for retesting.

Determine if the XRF testing in the units or house passed or failed the test by applying the steps below. Compute the Retest Tolerance Limit by the following steps:

Determine XRF results for the original and retest XRF readings. In single-family and multi-family housing, a result is defined as a single reading. Therefore, there will be ten original and ten retest XRF results for each house or for the two selected units.

Calculate the average of the original XRF result and the retest XRF result for each testing combination.

Square the average for each testing combination.

Add the ten squared averages together. Call this quantity C.

Multiply the number C by 0.0072. Call this quantity D.

Add the number 0.032 to D. Call this quantity E.

Take the square root of E. Call this quantity F.

Multiply F by 1.645. The result is the Retest Tolerance Limit.

Compute the average of all ten original XRF readings.

Compute the average of all ten re-test XRF readings.

Find the absolute difference of the two averages.

If the difference is less than the Retest Tolerance Limit, the inspection has passed the retest. If the difference of the overall averages equals or exceeds the Retest Tolerance Limit, this procedure should be repeated with ten new testing combinations. If the difference of the overall

averages is equal to or greater than the Retest Tolerance Limit a second time, then the inspection should be considered deficient.

Use of this procedure is estimated to produce a spurious result approximately 1% of the time. That is, results of this procedure will call for further examination when no examination is warranted in approximately 1 out of 100 dwelling units tested.

#### **TESTING TIMES:**

The reading time in Archive tests averaged 10 seconds.

#### **CLASSIFICATION OF RESULTS:**

XRF results to two decimal places are classified as **positive** if they are **greater than or equal** to 0.38 mg/cm<sup>2</sup>, **negative** if they are **less than or equal** to 0.29 mg/cm<sup>2</sup> and **inconclusive** if they are **greater** than 0.29 mg/cm<sup>2</sup> **AND less than** 0.38 mg/cm<sup>2</sup>.

#### **DOCUMENTATION:**

A report titled *Methodology for XRF Performance Characteristic Sheets* (EPA 747-R-95-008) provides an explanation of the statistical methodology used to develop Performance Characteristic Sheets at the Federal standard (Action Level) of 1.0 mg/cm<sup>2</sup> and provides empirical results from using the recommended inconclusive ranges or thresholds for specific XRF instruments. The report may be downloaded at <http://www2.epa.gov/lead/methodology-xrf-performance-characteristic-sheets-epa-747-r-95-008-september-1997>. The methodology was subsequently generalized by QuanTech for application to other Action Levels.